

Abstract of the Disclosure:

In a dielectric material for a plasma display panel including 80-100 mass% glass powder and 0-20 mass% ceramic powder, the glass powder consists essentially of, in mass percent, 3-25% BaO, 25-60% ZnO, 15-35% B₂O₃, 3-30% SiO₂, 0.2-6% Li₂O, and 0-1.5% Al₂O₃.